

MOPLY N FV 2 mm

MOPLY N FV 2 MM is an admixed APP plastomeric bitumen-based waterproofing membrane, with a low-temperature flexibility of \square -5°C , reinforced with glass fibre veil (FV), and finished with thermofusible film on both sides.

ADVANTAGES

- MOPLY FV is manufactured with an APP plastomeric compound, which confers the following properties to the membrane:
 - Great toughness.
 - Good low temperature pliability.
 - Great resistance against atmospheric agents and a maximum guarantee of durability.
 - High softening point; it is a tough membrane, with high temperature resistance and easy application even in hot weather.
- The glass fibre veil (FV) reinforcement confers maximum dimensional stability to the membrane.



APPLICATION

Suitable for most waterproofing slope roofing applications.

MOPLY N FV is applied in a multiple-ply system on non-trafficable roofs and roofs allowing foot traffic as base sheet, with a pitch of between 1% and 15%. On slopes exceeding 5%, the membrane must be fully bonded to the substrate.

Does not required a heavy protection on top of it.

REGULATIONS

- According to EN 13707 European standard. Certified under CE N° 0099/CPR/A85/0087
- Quality Management system according to ISO:9001 standard.

Bituminous Waterproofing APP

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

INSTALLATION

- **SUBSTRATE:** the substrate receiving the membrane must be dry, firm, even, clean and free from badly adhered materials.
- The membrane can be applied either fully bonded or loose-laid, depending on the system and slope. In the two-ply system, the membranes must be fully bonded to each other, and on self-protected roofs (without heavy topping) the base membrane must always be adhered to the substrate.
- Prior to adhering the membrane to the substrate, the latter must be primed with either PREJUNTER HD-1, PIBIAL or EMUFAL I.
- Once dry, the membrane is torched on. Overlaps are flame-bonded, with minimum 8-cm width.
- The membranes are installed in such a way that no more than three membranes overlap at the same point.

Bituminous Waterproofing APP

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

PACKAGING AND STORAGE

	MOPLY N FV 2 mm	MOPLY N FV 3 mm	MOPLY N FV 4 mm
Kg/m ²	--	--	--
Thickness (mm)	2,00 ± 0,2	3,00 ± 0,2	4,00 ± 0,2
Length (m)	15	11	8
Width (m)	1	1	1
m ² /roll	15	11	8
m ² /pallet	405	275	200

Storage: Upstand. Sheet must be stored into its original packaging until it has been used, protected against weathering, indoors in a ventilated area.

TECHNICAL PROPERTIES

CHARACTERISTICS	Test Method	Unit	MOPLY N FV 2 mm
External fire behaviour	ENV 1187	-	Broof(t1)
Fire reaction	EN 13501-1:2002 (EN ISO 11925-2)	-	E
Watertightness	EN 1928:2000 (B)	-	Pass (10 kPa)
Maximum tensile strength (L x T)	EN 12311-1	N/50 mm	350 ± 100 250 ± 100
Elongation (L x T)	EN 12311-1	%	NPD
Root penetration resistance	EN 13948	-	NE
Static load resistance	EN 12730 (A)	kg	NPD
Impact resistance	EN 12691:2006	mm	NPD
Tear strength (nail) (L x T)	EN 12310-1	N	NE
Joint peel resistance	EN 12316-1	N/50 mm	NE
Joint shear resistance (L x T)	EN 12317-1	N/50 mm	NE
Artificial ageing by long-term exposure to high temperature	EN 1296 12 sem/weeks	EN 1109 / 1110	NE
Artificial ageing by long term exposure to the combination of UV radiation, high temperature and water	EN 1297	EN 1850-1	NE
Flexibility at low temperature	EN 1109	°C	≤ -5
Hazardous substances	--	--	PND

Bituminous Waterproofing APP

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

OTHER FEATURES

OTHER CHARACTERISTICS	Test Method	Unit	Value
Visible defects	EN 1850-1	-	Pass
Straightness	EN 1848-1	-	Pass (<20 mm/10 m)
Compound per area unit	EN 1849-1	kg/m ²	--
Thickness	EN 1849-1	mm	2 ±0,2
Thickness in overlap	EN 1849-1	mm	-
Watertightness after stretching at low temperature	EN 13897	%	--
Dimensional stability	EN 1107-1	%	NE
Form stability under cyclic temperature change	EN 1108	mm	NE
High temperature flow resistance	EN 1110	°C	≥ 70
Granule adhesion	EN 12039	%	NE
Water vapour transmission properties	EN 1931	μ	20000

Bituminous Waterproofing APP

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.