

TEXSALON MP SC

TEXSALON MP SC is a synthetic membrane manufactured in TPO modified polyolefin, obtained by co-extrusion, reinforced by a polyester mesh.

The upper light grey layer is featured by a very high resistance to weather and UV rays, while the underlying black layer is punching resistant.

ADVANTAGES

- Weatherproof and UV resistance
- Resistant to wind stress.
- Mechanical resistance and resistance to punching
- Adaptability to structural movements
- Flexibility at low temperatures
- Excellent welding capacity

APPLICATION

TEXSALON MP SC is used for roof waterproofing:

- Exposed roof, with mechanical fastening system
- Independents systems in inverted roofs
- Ballasted with fixed and mobile ballast

REGULATIONS

- Quality Management System according to the requirements of ISO 9001:2008 standard and environmental management system ISO 14001.
- Complies with standard EN 13956. Certificate CE nº 1085/CPR/0263.
- Product approved by FM (Factory mutual)

Synthetic Waterproofing TPO

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

PACKAGING AND STORAGE

	TEXSALON MP SC 1.5	TEXSALON MP SC 1.5	TEXSALON MP SC 1.8	TEXSALON MP SC 1.8	TEXSALON MP SC 2.0	TEXSALON MP SC 2.0
Roll length (m)	20	20	20	20	20	20
Roll width (m)	1.05	2.10	1.05	2.10	1.05	2.10
m2/roll	21	42	21	42	21	42
m2/pallet	966	966	756	756	756	756
Upper layer colour	light grey	light grey	light grey	light grey	light grey	light grey
Underside layer colour	Black	Black	Black	Black	Black	Black

Storage: Horizontally, parallel (never crossed) Store in the original packaging in a dry and cool place

Synthetic Waterproofing TPO

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

TECHNICAL PROPERTIES

PROPERTIES	Unit	Test Method	TEXSALON MP SC 1.5	TEXSALON MP SC 1.8	TEXSALON MP SC 2.0
Thickness	mm	EN 1849-2	1.5	1.8	2.0
Weight	Kg/m ²	EN 1849-2	1.90	2.28	2.54
Tensile strength	N/5cm	EN 12311-2	≥ 1100	≥ 1100	≥ 1100
Elongation to break	%	EN 12311-2	≥ 15	≥ 15	≥ 15
Tear resistance	N	EN 12310-2	≥ 300	≥ 300	≥ 300
Resistance to impact	mm	EN 12691	≥ 800	≥ 900	≥ 1250
Joint peel resistance	N/50mm	EN 12316-2	≥ 200	≥ 200	≥ 200
Joint shear resistance	N/5cm	EN 12317-2	> 600	> 600	> 600
Cold bending	°C	EN 495-5	≤ - 25	≤ - 25	≤ - 25
Hydrostatic pressure resistance (6 hours at 0.5 Mpa)		EN 1928 (B)	Waterproofing	Waterproofing	Waterproofing
Dimensional stability	%	EN 1107-2	≤ 0.5	≤ 0.5	≤ 0.5
Resistance to artificial weathering	U.V.	EN 1297	No surface cracking	No surface cracking	No surface cracking
Resistance to root penetration		UNE 13948	No penetration	No penetration	No penetration
Resistance to static punching	kg	EN 12730 (B)	≥ 20	≥ 20	≥ 20
Fire behavior*	class	EN 13501-5	B roof t2 B roof t3	B roof t2 B roof t3	B roof t2 B roof t3
Fire resistance	class	EN ISO 11925-2 EN13501-1	E	E	E

* classification valid only for the application of the membrane for systems as indicated by certification available on request.

Synthetic Waterproofing TPO

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.