

MOPLY N PLUS FV 3 KG

MOPLY N PLUS FV 3 KG is a non-self-protected membrane, made of APP plastomeric bitumen with polymer additives with low temperature plegability of \geq -10 $^{\circ}$ C, reinforced with glass fibre felt (FV), and finished with a thermally bonded film on both the upper and lower side.

ADVANTAGES

- · In the system, it improves the features of the primary membrane by providing excellent dimensional stability, especially if the primary membrane is reinforced with Polyethylene PE (polyolefins) or polyester felt FP.
- · Replaces the oxyasphalt membrane by providing a less contaminating production process and results in:
- A mastic with plastic features that allow for easy placement and handling.
- Better performance at high temperatures and better flexibility (-10°C), provides the membrane with a slower ageing process.



APPLICATION

- · Application as a complementary membrane in single-layer trafficable or non-trafficable systems with heavy protection used with a primary membrane equal to or greater than 4 kg from the MORTERPLAS or MORTERPLAS SBS (LBM) line.
- · A complementary membrane in self-protected roof systems used with a primary membrane from the MORTERPLAS MIN or MORTERPLAS SBS MIN (LBM) line.
- As complementary membranes in green roof systems used with a MORTERPLAS GARDEN MIN primary membrane or a double-layer membrane made of LBM membranes whose top MORTERPLAS FP 4kg GARDEN membrane has anti-root protection.
- · As an emergency or auxiliary membrane when provisional waterproofing may be required.
- · Waterproofing of foundations, basements, etc. by complementing the membranes used with LBM membranes
- · Base membrane in multi-layer waterproofing.

REGULATIONS

- · In accordance with the EN 13707 standard. Certified with CE marking No. 0099/CPD/A85/0087
- · Voluntary certification of the product with AENOR seal according to the same European standard.
- · Quality System in accordance with ISO:9001

Bituminous Waterproofing APP

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.



INSTALLATION

- \cdot SUPPORT: The surface must be dry, firm, even, clean and free of loose materials.
- · It can be applied completely adhered, partially adhered or floating.
- \cdot To adhere the membrane to the support, the support is primed with EMUFAL I or EMUFAL L. Once dry, use flame to adhere the membrane.
- \cdot The flame is applied as uniformly as possible (the greater the heat, the greater the retraction) along the width of the membrane without reaching the overlap, which will be done later, since it is important that the temperature be the same in every area. The flame should be applied until the anti-adherent film pore opens.
- \cdot The membranes are installed in such a way that no more than three membranes overlap at the same point.
- · Overlaps are flame-bonded, with a minimum overlap of 8 cm.
- · The top membrane must be completely adhered to the bottom membrane, and it must be placed in the same direction and so that the overlap lays approximately in the middle of the bottom membrane.
- · Installation and measurements will be conducted in accordance with european regulations and the Texsa application guide.

Bituminous Waterproofing APP

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.



PACKAGING AND STORAGE

	MOPLY N PLUS FV 4 Kg	MOPLY N PLUS FV 3 Kg	
Kg/m²	4 (-5/+10%)	3 (-5/+10%)	
Length (m)	10	13	
Width (m)	1	1	
m2/roll	10	13	
m2/pallet	270	351	

Storage: Upright on pallet. Store in the original packaging in a dry and cool place, protected against weathering.

TECHNICAL PROPERTIES

TECHNICAL PROPERTIES			
CHARACTERISTICS	Test Method	Unit	MOPLY N PLUS FV 3 KG
External fire behaviour	ENV 1187	-	Broof(t1)
Fire reaction	EN 13501-1:2002 (EN ISO 11925-2)	-	E
Watertightness	EN 1928:2000 (B)	-	Pass (10 kPa)
Maximum tensile strength (L x T)	EN 12311-1	N/50 mm	350 ± 100 250 ± 100
Elongation (L x T)	EN 12311-1	%	NPD
Root penetration resistance	EN 13948	-	NE
Static load resistance	EN 12730 (A)	kg	NPD
Impact resistance	EN 12691:2006	mm	NPD
Tear strength (nail) (L x T)	EN 12310-1	N	NE
Joint peel resistance	EN 12316-1	N/50 mm	NE
Joint shear resistance (L x T)	EN 12317-1	N/50 mm	NE
Artificial ageing by long-term exposure to high temperature	EN 1296 12 sem/weeks	EN 1109 / 1110	NE
Artificial ageing by long term exposure to the combination of UV radiation, high temperature and water	EN 1297	EN 1850-1	NE
Flexibility at low temperature	EN 1109	ōС	≤ -10
Hazardous substances			PND

OTHER FEATURES

OTHER CHARACTERISTICS	Test Method	Unit	Value
Visible defects	EN 1850-1	-	Pass
Straightness	EN 1848-1	-	

Bituminous Waterproofing APP

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.